

Rigid Core

PLANKS NAPA FROSTY WHITE





Specification

NI		
N		

Surface finishing	UV cured acrylic
Colour	Frosty white
Pattern	Plank
Locking system	5G Dry
Core	SPC - Rigid polymeric core
Microbevel	4 sided micro bevel

DIMENSIONS

Width	228 mm
Width (ISO 24337)	9"
Length	1830 mm
Length (ISO 24337)	72"
Thickness	6.5 mm
Thickness (ASTM F387)	1/4"
Thickness of wear layer	20 mil (0,55 mm)
Thickness of wear layer (ASTM F410)	0.02"

PACKAGE

Quantity in box	5
m² / box	2,09 m²
sq.ft per box	22.47 sqft
m² per pallet	100,2 m ²
sq.ft per pallet	1078.4 sqft
Weight per m²	9,13 kg
Weight per sq.ft	1.87 lbs
Weight per box	19.7 kg
Weight per box	43.33 lbs

CLASSIFICATION AND SAFETY

Greenguard Gold Certified	Greenguard Gold
Pass - max < 0.2%/linear ft (305 mm)	Dimensional stabillity (ISO 23999)
Pass - <1 mm	Curling (ISO 23999)
Pass - 25 000 rev	Effect of Castor Chair (ISO 4918)
Pass - <0.18 mm(34 kg, 6.35 mm flat foot)	Residual indentation (ASTM F1914)
Pass - <0.13 mm indent, 250 lb/N2	Static load (ASTM F970)
No puncture through wear layer/decor into core	Surface integrity (ASTM F1914)
Pass	Resistance to chemicals (ASTM F925)
Pass	Resistance to heat (ASTM F1514)
Pass	Resistance to light (ASTM F1515)
Dry: >0.6	Static coefficient of friction (ASTM D2047)
Class 1 : ≥ 0.45 W/cm²	Critical Radiant flux (ASTM E648)
Greenguard Gold Certified	Sustainabillity VOC
Pthalates and heavy metals below the detection limit	Phthalates & heavy metals
54	Sound transmission class (ASTM F90)
53	Impact insulation class
20	Sound transmission reduction (ASTM E2179)

MISC.	
Water Resistance	High
Construction	SPC - Rigid polymeric core - modular resillient flooring
Product Specification	ASTM F3261-17 Class I, Type B, Grade 1, Backing class B
Installation method	Floating 5G Dry
Limited Warranty (Public Environment)	15 years
Limited Warranty (Domestic Environment)	Limited lifetime warranty
Level of use domestic (EN ISO 10874)	Class Heavy Residential
Level of use commercial (EN ISO 10874)	Class Heavy Commercial



Bjelin Sweden AB bjelin.com support@bjelin.se +46-771-101099