

Woodura Planks 3.0

VIARP 3.0 L

Vrsta drveta
HrastKlase
NaturePovršinska obrada
Četkani mat lakOtpornost na vodu
Visoka

Prostoriju koju želite osvežiti. Boja Powder White savršena je za minimalistički i moderni dizajn interijera.



Specifikacija

OPĆENITO

| | |
|--------------------|-----------------|
| Vrsta podne obloge | Učvršćeno drvo |
| Vrsta drveta | Hrast |
| Klase | Nature |
| Površinska obrada | Četkani mat lak |
| Boja | Powder White |
| Svijetlo/tamno | Svijetlo |
| Uzorak | Podna daska |
| Spoj | Välinge 5G Dry@ |
| Jezgra | HDF |

DIMENZIJE

| | |
|------------------------|---------|
| Format | L |
| Širina | 180 mm |
| Dužina | 2030 mm |
| Visina | 9,2 mm |
| Debljina gornjeg sloja | 0,6 mm |

PAKET

| | |
|--------------------------|-----------------------|
| Količina u paketu | 7 |
| m ² / paket | 2,562 m ² |
| m ² po paleti | 92,232 m ² |
| Težina po m ² | 8,940 kg |
| Težina po paketu | 23,06 kg |

KLASIFIKACIJA I SIGURNOST

| | |
|--|--|
| Podržava podno grijanje | Da |
| Otpornost na vodu | Visoka |
| Otpornost na vatru (EN 13501) | Cfl-S1 |
| Toplinska vodljivost (EN 12664) | 0,12 W/(m*K) |
| Toplinska otpornost (EN 12667) | 0,075 (m ² x K)/W |
| Emisija formaldehida (EN 717-1) | Emisija formaldehida.E1 <=0,1 ppm (tipična vrijednost <= 0,05 ppm) |
| Ocjena tvrdoće (EN 1534) | 8 HB (average value) |
| Otpornost na udarce (EN 14354) | EC3 |
| Debljina oticanja (EN 14354) | <10% (5% tipično) |
| Otpornost na habanje (EN 14354) | > 1000 ciklusa |
| Otpor na klizanje (USRV) (CEN//TS 15676) | 40 |
| FSC | FSC Mix (FSC-C140725) |
| A+ | Yes |
| M1 | Yes |
| CE označeno | Da |
| Ograničeno jamstvo (javno okruženje) | 30 godine |
| Ograničeno jamstvo (kućno okruženje) | 30 godine |
| Razina kućne upotrebe (EN ISO 10874) | Class Moderate residential (Class 22) |

RAZNO

| | |
|-------------|---|
| Revision nr | 1 |
|-------------|---|



woodura®

Bjelin Croatia d.o.o | bjelin.com | hr-sales@bjelin.com

Copyright 2026 Bjelin Sweden AB. Weights and dimensions may have minor variations depending on external circumstances. Bjelin reserves the right to deviate from the weight and dimensions in this technical data sheet. Technologies mentioned may be subject to patent protection and invented by Välinge Innovation AB (www.valinge.se/patents). Use of trademarks herein owned by Bjelin Sweden AB or Välinge Innovation AB is under license.



Za upute o postavljanju i održavanju te daljnje informacije o proizvodu skenirajte QR kod ili posjetite bjelin.com.